



PRODUCT DATA SHEET **CURLEX® II CL**

DESCRIPTION

Curlex II CL erosion control blanket (ECB) consists of a specific cut of naturally seed free Great Lakes Aspen curled wood excelsior with 80% six-inch fibers or greater fiber length. It is of consistent thickness with fibers evenly distributed throughout the entire area of the blanket. The top and bottom of each blanket is covered with degradable polypropylene netting. Curlex II CL is also available as QuickGRASS® (Dyed Green). Curlex II CL shall be manufactured in the U.S.A.

Curlex II CL has a design soil loss ratio (event-based RUSLE C factor) of .050 and is typically suitable for slopes up to 1.5H:1V. Curlex II CL is rated for channel flows up to 7.3 ft/s (2.2 m/s) and 1.80 lb/ft² (86 Pa) shear stress.

PHYSICAL PROPERTIES

Curlex II CL measurements at time of manufacturing:

Width	4.0 ft (1.2 m)	8.0 ft (2.4 m)	16.0 ft (4.9 m)
Length	150.0 ft (45.7 m)	150.0 ft (45.7 m)	150.0 ft (45.7 m)
Area	66.7 yd ² (55.7 m ²)	133.3 yd ² (111.5 m ²)	266.7 yd ² (223.0 m ²)
Weight¹	36.7 lb (16.6 kg)	73.3 lb (33.3 kg)	146.7 lb (65.5 kg)
Fiber Count	≈4,800 per yd ² (≈5,760 per m ²)	≈4,800 per yd ² (≈5,760 per m ²)	≈4,800 per yd ² (≈5,760 per m ²)
Fiber Length (80% min.)	≥6.0 in (≥15.2 cm)	≥6.0 in (≥15.2 cm)	≥6.0 in (≥15.2 cm)
Mass per Unit Area (± 10%)	0.55 lb/yd ² (0.30 kg/m ²)	0.55 lb/yd ² (0.30 kg/m ²)	0.55 lb/yd ² (0.30 kg/m ²)
Net Openings	1.0 in x 2.0 in (25.4 mm x 50.8 mm)	1.0 in x 2.0 in (25.4 mm x 50.8 mm)	1.0 in x 2.0 in (25.4 mm x 50.8 mm)

TYPICAL INDEX VALUES

<u>Index Property</u>	<u>Test Method</u>	<u>Value</u>
Thickness	ASTM D 6525	0.364 in (9.25 mm)
Light Penetration	ASTM D 6567	44%
Mass per Unit Area	ASTM D 6475	0.40 lb/yd ² (217 g/m ²)
MD-Tensile Strength Max.	ASTM D 6818	128.4 lb/ft (1.87 kN/m)
TD-Tensile Strength Max.	ASTM D 6818	45.6 lb/ft (0.67 kN/m)
MD-Elongation	ASTM D 6818	38.9%
TD-Elongation	ASTM D 6818	23.1%
Swell	ECTC Procedure	49%
Water Absorption	ASTM D 1117/ECTC	189%
Bench-Scale Rain Splash	ECTC Method 2	SLR = 7.06 @ 2 in/hr ^{2,3}
Bench-Scale Rain Splash	ECTC Method 2	SLR = 5.94 @ 4 in/hr ^{2,3}
Bench-Scale Rain Splash	ECTC Method 2	SLR = 5.00 @ 6 in/hr ^{2,3}
Bench-Scale Shear	ECTC Method 3	1.95 lb/ft ² @ 0.5 in soil loss ³
Germination Improvement	ECTC Method 4	429%

¹ Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.

² SLR is the Soil Loss Ratio, as reported by NTPEP/AASHTO. ³ Bench-scale index values should not be used for design purposes.

