



PRODUCT DATA SHEET
TRINET® COCONUT

DESCRIPTION

TriNet Coconut is a three dimensional biocomposite turf reinforcement mat (TRM) that consists of a coconut fiber matrix. The fibers are evenly distributed throughout the entire area of the TRM. The top, middle, and bottom nets of each TRM are stitched together forming a permanent three dimensional TRM. TriNet Coconut shall be manufactured in the U.S.A.

TriNet Coconut has a design soil loss ratio (event-based RUSLE C factor) of .031 and is typically suitable for slopes up to .5H:1V. TriNet Coconut is rated for channel flows up to 20.0 ft/s (6.1 m/s) and 12 lb/ft² (575 Pa) shear stress.

PHYSICAL PROPERTIES

TriNet Coconut measurements at time of manufacturing:

Width		8.0 ft (2.4 m)	16.0 ft (4.9 m)
Length		90.0 ft (27.4 m)	90.0 ft (27.4 m)
Area		80.0 yd ² (66.9 m ²)	160.0 yd ² (133.8 m ²)
Weight^a		66.6 lb (30.2 kg)	133.3 lb (60.46 kg)
Coconut Matrix (± 10%)		0.500 lb/yd ² (0.271 kg/m ²)	0.500 lb/yd ² (0.271 kg/m ²)
Product Weight (± 10%)		0.833 lb/yd ² (0.452 kg/m ²)	0.833 lb/yd ² (0.452 kg/m ²)
Net Openings	Top - Super Heavy Duty Polypropylene (UV-Stabilized)	0.5 in x 0.5 in (12.7 mm x 12.7 mm)	0.5 in x 0.5 in (12.7 mm x 12.7 mm)
	Middle - Ultra Heavy Duty Polypropylene (UV-Stabilized)	0.454 in x 0.588 in (11.54 mm x 14.94 mm)	0.454 in x 0.588 in (11.54 mm x 14.94 mm)
	Bottom - Super Heavy Duty Polypropylene (UV-Stabilized)	0.5 in x 0.5 in (12.7 mm x 12.7 mm)	0.5 in x 0.5 in (12.7 mm x 12.7 mm)

TYPICAL INDEX VALUES

<u>Index Property</u>	<u>Test Method</u>	<u>Value</u>
Thickness	ASTM D 6525	0.264 in (6.71 mm)
Light Penetration	ASTM D 6567	16.5%
Resiliency	ASTM D 1777/ECTC	89%
Mass per Unit Area	ASTM D 6475	0.69 lb/yd ² (0.374 kg/m ²)
MD-Tensile Strength Max.	ASTM D 6818	712.8 lb/ft (10.4 kN/m)
TD-Tensile Strength Max.	ASTM D 6818	703.2 lb/ft (10.3 kN/m)
MD-Elongation	ASTM D 6818	18.9%
TD-Elongation	ASTM D 6818	17.2%
Swell	ECTC Procedure	18%
Water Absorption	ASTM D 1117/ECTC	244.3%
Specific Gravity	ASTM D 792	0.915
UV Stability	ASTM D 4355 (1,000 hr)	90% minimum
Porosity	ECTC Procedure	95.58%
Stiffness	ASTM D6575	1.53 oz-in

^a Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Coconut fibers is 20%.

