



**PRODUCT DATA SHEET**  
**CURLEX® HIGH VELOCITY™ FIBRENET™**

**DESCRIPTION**

Curlex High Velocity (HV) FibreNet erosion control blanket (ECB) consists of a specific cut of naturally seed free Great Lakes Aspen curled wood excelsior with 80% six-inch fibers or greater fiber length. It is of consistent thickness with fibers evenly distributed throughout the entire area of the blanket. The top and bottom of each blanket is covered with 100% biodegradable jute netting. The products is 100% biodegradable when biodegradable thread is ordered. Curlex High Velocity FibreNet is also available as QuickGRASS® (green pigment). Curlex High Velocity FibreNet shall be manufactured in the U.S.A.

Curlex High Velocity FibreNet has a design soil loss ratio (event-based RUSLE C factor) of .022 and is typically suitable for slopes up to .75H:1V. Curlex HV is rated for channel flows up to 11 ft/s (3.4 m/s) and 3.25 lb/ft<sup>2</sup> (156 Pa) shear stress.

**PHYSICAL PROPERTIES**

Curlex High Velocity FibreNet measurements at time of manufacturing:

<b>Width</b>	4.0 ft (1.2 m)	8.0 ft (2.4 m)
<b>Length</b>	100.0 ft (30.5 m)	50.0 ft (15.2 m)
<b>Area</b>	44.4 yd <sup>2</sup> (37.1 m <sup>2</sup> )	44.4 yd <sup>2</sup> (37.1 m <sup>2</sup> )
<b>Weight<sup>a</sup></b>	71.9 lb (32.6 kg)	71.9 lb (32.6 kg)
<b>Fiber Count</b>	≈15,500 per yd <sup>2</sup> (≈18,600 per m <sup>2</sup> )	≈15,500 per yd <sup>2</sup> (≈18,600 per m <sup>2</sup> )
<b>Fiber Length (80% min.)</b>	≥6.0 in (≥15.2 cm)	≥6.0 in (≥15.2 cm)
<b>Mass per Unit Area (± 10%)</b>	1.62 lb/yd <sup>2</sup> (0.88 kg/m <sup>2</sup> )	1.62 lb/yd <sup>2</sup> (0.88 kg/m <sup>2</sup> )
<b>Net Openings</b>	0.5 in x 1.0 in (12.7 mm x 25.4 mm)	0.5 in x 1.0 in (12.7 mm x 25.4 mm)

**TYPICAL INDEX VALUES**

<u>Index Property</u>	<u>Test Method</u>	<u>Value</u>
Thickness	ASTM D 6525	0.377 in (9.58 mm)
Light Penetration	ASTM D 6567	7.8%
Resiliency	ASTM D 1777/ECTC	53%
Mass per Unit Area	ASTM D 6475	1.276 lb/yd <sup>2</sup> (0.692 kg/m <sup>2</sup> )
MD-Tensile Strength Max.	ASTM D 6818	232.8 lb/ft (3.4 kN/m)
TD-Tensile Strength Max.	ASTM D 6818	178.8 lb/ft (2.61 kN/m)
MD-Elongation	ASTM D 6818	8.1%
TD-Elongation	ASTM D 6818	12.6%
Swell	ECTC Procedure	48%
Water Absorption	ASTM D 1117/ECTC	244%
Bench-Scale Rain Splash	ASTM D 7101	SLR = 17.97 @ 2 in/hr <sup>b,c</sup>
Bench-Scale Rain Splash	ASTM D 7101	SLR = 22.70 @ 4 in/hr <sup>b,c</sup>
Bench-Scale Rain Splash	ASTM D 7101	SLR = 12.89 @ 6 in/hr <sup>b,c</sup>
Bench-Scale Shear	ASTM D 7207	5.15 lb/ft <sup>2</sup> @ 0.5 in soil loss <sup>c</sup>
Germination Improvement	ASTM D 7322	742%

<sup>a</sup> Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.

<sup>b</sup> SLR is the Soil Loss Ratio, as reported by NTPEP/AASHTO. <sup>c</sup> Bench-scale index values should not be used for design purposes.

