



## MATERIAL SPECIFICATIONS CURLEX® II (.98)

### Materials:

Great Lakes Aspen (naturally seed free)  
Polypropylene Netting  
Stitching Thread  
QuickGRASS® (green excelsior – optional)

### Typical Roll Sizes:

Width:	4.0 ft (1.2 m)	8.0 ft (2.4 m)	16.0 ft (4.9 m)
Length:	90.0 ft (27.4 m)	90.0 ft (27.4 m)	90.0 ft (27.4 m)
Area:	40.0 yd <sup>2</sup> (33.4 m <sup>2</sup> )	80.0 yd <sup>2</sup> (66.9 m <sup>2</sup> )	160.0 yd <sup>2</sup> (133.8 m <sup>2</sup> )
Weight:	39.2 lb (17.8 kg)	78.4 lb (35.6 kg)	156.8 lb (71.2 kg)

### Description:

Curlex II .98 erosion control blanket (ECB) is a natural, stitched excelsior blanket that provides a temporary organic cover to reduce erosion, protect seeds, enhance germination, and hasten re-vegetation. Curlex II .98 is furnished in rolls with polyethylene wrapping to protect against the elements prior to installation, and may be ordered in Master-Paks of fifteen rolls banded together to minimize material handling requirements. Curlex II .98 is also available as QuickGRASS (green pigment). Curlex II .98 shall be manufactured in the U.S.A.

Curlex II .98 has a design soil loss ratio (event-based RUSLE C factor) of .022 and is typically suitable for slopes up to 1H:1V. Curlex II .98 is rated for channel flows up to 10.0 ft/s (3.1 m/s) and 2.5 lb/ft<sup>2</sup> (120 Pa) shear stress.

### Physical Properties:

Fiber:	Great Lakes Aspen (naturally seed free) Curled, interlocking fibers with barbed edges
Fiber Size:	80% of fibers a minimum of 6 in (15.2 cm) long 0.038 in ± 0.008 in wide x 0.018 in ± 0.003 in thick (0.97 mm ± 0.20 mm wide x 0.46 mm ± 0.08 mm thick)
Weight <sup>a</sup> :	0.98 lb/yd <sup>2</sup> (0.53 kg/m <sup>2</sup> ) ± 10% @ 22% Moisture
Thread Pattern:	No more than 4.0 in (10.2 cm) transverse stitch spacing
Net Material:	Polypropylene (green with oxo-biodegrader and UV degrader additives or white with UV degrader additive)
Net Openings:	1.0 in wide x 2.0 in long (25.4 mm wide x 50.8 mm long)
Net Configuration:	Top and bottom

<sup>a</sup> Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%





**MANUFACTURER'S CERTIFICATION**  
**CURLEX® II (.98) – Erosion Control Blanket**

**Manufacturer:**

American Excelsior Company  
831 Pioneer Avenue  
Rice Lake, WI 54868  
1-866-9FIBERS (1-866-934-2377)

**Project Information (if applicable):**

**Name:**

**Location:**

**Number:**

**Statement**

We hereby certify that the above referenced material is manufactured to meet or exceed the following specification:

Fiber:	Great Lakes Aspen (naturally seed free) Curled, interlocking fibers with barbed edges
Fiber Size:	80% of fibers a minimum of 6 in (15.2 cm) long 0.038 in $\pm$ 0.008 in wide x 0.018 in $\pm$ 0.003 in thick (0.97 mm $\pm$ 0.20 mm wide x 0.46 mm $\pm$ 0.08 mm thick)
Blanket Length:	-0 ft (m) + 2.0 ft (0.6 m)
Blanket Width:	-0 in (mm) + 1.0 in (25.4 mm)
Weight <sup>a</sup> :	0.98 lb/yd <sup>2</sup> (0.53 kg/m <sup>2</sup> ) $\pm$ 10% @ 22% Moisture
Thread Pattern:	No more than 4.0 in (10.2 cm) transverse stitch spacing
Net Material:	Polypropylene (green with oxo-biodegrader and UV degrader additives or white with UV degrader additive)
Net Openings:	1.0 in wide x 2.0 in long (25.4 mm wide x 50.8 mm long)
Net Configuration:	Top and bottom

<sup>a</sup> Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%

TJ 4.4

Tony Johnson – General Manager, Rice Lake

Effective Date

**Note:** This Certification expires, without notice, if document is updated by American Excelsior Company (AEC). Current Material Specifications and Manufacture's Certifications (MSMC) for AEC products shall be accessed from [www.Curlex.com](http://www.Curlex.com) at all times.

