



PRODUCT DATA SHEET **CURLEX® III FIBRENET™**

DESCRIPTION

Curlex III FibreNet erosion control blanket (ECB) consists of a specific cut of naturally seed free Great Lakes Aspen curled wood excelsior with 80% six-inch fibers or greater fiber length. It is of consistent thickness with fibers evenly distributed throughout the entire area of the blanket. The top and bottom of each blanket is covered with 100% biodegradable jute netting. The product is 100% biodegradable when biodegradable thread is ordered. Curlex III FibreNet is also available as QuickGRASS® (green pigment). Curlex III FibreNet shall be manufactured in the U.S.A.

Curlex III FibreNet has a design soil loss ratio (event-based RUSLE C factor) of .022 and is typically suitable for slopes up to 1H:1V. Curlex III FibreNet is rated for channel flows up to 10.0 ft/s (3.1 m/s) and 2.5 lb/ft² (120 Pa) shear stress.

PHYSICAL PROPERTIES

Curlex III FibreNet measurements at time of manufacturing:

Width	4.0 ft (1.2 m)	8.0 ft (2.4 m)	16.0 ft (4.9 m)
Length	90.0 ft (27.4 m)	90.0 ft (27.4 m)	90.0 ft (27.4 m)
Area	40.0 yd ² (33.4 m ²)	80.0 yd ² (66.9 m ²)	160 yd ² (133.8 m ²)
Weight ^a	39.2 lb (17.8 kg)	78.4 lb (35.6 kg)	156.8 lb (71.2 kg)
Fiber Count	≈9,400 per yd ² (≈11,280 per m ²)	≈9,400 per yd ² (≈11,280 per m ²)	≈9,400 per yd ² (≈11,280 per m ²)
Fiber Length (80% min.)	≥6.0 in (≥15.2 cm)	≥6.0 in (≥15.2 cm)	≥6.0 in (≥15.2 cm)
Mass per Unit Area (± 10%)	0.98 lb/yd ² (0.53 kg/m ²)	0.98 lb/yd ² (0.53 kg/m ²)	0.98 lb/yd ² (0.53 kg/m ²)
Net Openings	≈ 0.5 in x 1.0 in (12.7 mm x 25.4 mm)	≈ 0.5 in x 1.0 in (12.7 mm x 25.4 mm)	≈ 0.5 in x 1.0 in (12.7 mm x 25.4 mm)

TYPICAL INDEX VALUES

Index Property	Test Method	Value
Thickness	ASTM D 6525	0.226 in (5.74 mm)
Light Penetration	ASTM D 6567	18.2%
Mass per Unit Area	ASTM D 6475	0.818 lb/yd ² (0.444 kg/m ²)
MD-Tensile Strength Max.	ASTM D 6818	252.0 lb/ft (3.68 kN/m)
TD-Tensile Strength Max.	ASTM D 6818	122.4 lb/ft (1.79 kN/m)
MD-Elongation	ASTM D 6818	8.4%
TD-Elongation	ASTM D 6818	13.8%
Water Absorption	ASTM D 1117/ECTC	268%
Bench-Scale Rain Splash	ASTM D 7101	SLR = 19.56 @ 2 in/hr ^{b,c}
Bench-Scale Rain Splash	ASTM D 7101	SLR = 27.36 @ 4 in/hr ^{b,c}
Bench-Scale Rain Splash	ASTM D 7101	SLR = 26.09 @ 6 in/hr ^{b,c}
Bench-Scale Shear	ASTM D 7207	3.48 lb/ft ² @ 0.5 in soil loss ^c
Germination Improvement	ASTM D 7322	975%

^a Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.

^b SLR is the Soil Loss Ratio, as reported by NTPEP/AASHTO. ^c Bench-scale index values should not be used for design purpose

